

Improv ments relating to cathode plate edge protectors

Patent Number: AU2561997

Publication date: 1997-11-19

Inventor(s): CONNOLLY RODGER

Applicant(s):: MARLEY PLASTICS PTY LTD

Requested
Patent: AU2561997

Application
Number: AU19970025619D 19970423

Priority Number AU1996PN09523 19960426; AU1996PO01065 19960716; WO1997AU00246 19970423;
(s): AU19970025619 19970423

IPC Classification: C25D11/00 ; C25C7/02 ; C25D17/10 ; B29D12/00

EC Classification:

Equivalents:

Abstract

Data supplied from the **esp@cenet** database - I2


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C25D 11/00, C25C 7/02, C25D 17/10, B29D 12/00		A1	(11) International Publication Number: WO 97/41280
			(43) International Publication Date: 6 November 1997 (06.11.97)
(21) International Application Number: PCT/AU97/00246		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(22) International Filing Date: 23 April 1997 (23.04.97)			
(30) Priority Data: PN 9523 26 April 1996 (26.04.96) AU PO 1065 16 July 1996 (16.07.96) AU			
(71) Applicant (for all designated States except US): MARLEY PLASTICS PTY. LTD. [AU/AU]; 19-21 Hallam Road South, Hallam, VIC 3803 (AU).			
(72) Inventor; and (75) Inventor/Applicant (for US only): CONNOLLY, Rodger [AU/AU]; 925 Nudgee Road, Nudgee, QLD 4014 (AU).			
(74) Agent: WATERMARK PATENT & TRADEMARK ATTORNEYS; 2nd floor, 290 Burwood Road, Hawthorn, VIC 3122 (AU).			

(54) Title: IMPROVEMENTS RELATING TO CATHODE PLATE EDGE PROTECTORS**(57) Abstract**

The use of cathode plates for electrolytic copper deposition, coupled with mouldings fitted for edge protection is well established. These include such things as edge strips, gripping edge protectors and dipping in wax, to prevent build-up of the plated metal along the edge portion. These edge protectors are quite effective along the sides, but attempts to fit protectors to the bottom edge of the plates have resulted in the build-up of copper in the gaps at the corner of the plate or the growth of copper nodules beneath the protecting strip, occasioned by thermal expansion and resultant small gaps at the joins. Wax, moreover, dissolves in hot electrolyte solution, causing a build-up of sludge in the refining tanks with substantial reduction in the life and efficiency of the electrolyte. These problems have been overcome by prefiting the cathode plate (10) with bottom (16) and side (11) edge plastic strips, in which the bottom (16) and side (11) edge plastic strips, together with the corner pieces (17), are integrally moulded together, the bottom edge corners of the plate being surrounded in the mould, prior to the injection of the plastic. Alternatively, the bottom and side edge strips (20) and the corner pieces (21) may be prefabricated, so that the corner pieces (21) lock into the plate by means of apertures and are either joined to the bottom and side edge portions (20) by plastic moulding of the corner piece (21) to the joint between the aforesaid bottom and side edge portions (20) or upper (22) and lower (23) wedge clips may be used to snap fit the corner moulding (21) and the bottom and side edge portions (20) together in sealing relationship.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

WO 97/41280

PCT/AU97/00246

1

IMPROVEMENTS RELATING TO CATHODE PLATE EDGE PROTECTORS

The present invention relates to edge strip protection for cathode plates and particularly to such protection of the corners of the cathode plate.

The use of cathode plates for electrolytic metal deposition particularly but
5 not exclusively copper, and other non-ferrous materials is well known.

To simplify removal of deposited metal from the cathode plate after the process, it is desirable to protect the side and bottom of the cathode plate with mouldings fitted to the edge portions; or by the application of wax to the edge portions to prevent build up of copper on the edge portions.

10 This facilitates the removal of the deposited metal.

Many disclosures occur in the patent literature in the field, for example AU Patent No. 646450 disclosing an edge strip with an expansion channel allowing for thermal expansion.

AU Patent No. 527416 disclosing a similar form of gripping edge protector
15 as being two examples of the prior art.

Alternative means of edge protection include dipping the edge of the cathode plate in a wax bath to prevent build up of metal along the edge portion.

This is used particularly for the bottom edge of the cathode plate and is depicted by way of example in Figure 1 of the drawings herewith.

20 In the process of refining copper and other non-ferrous metals, stainless steel cathode plates are suspended into an electrolyte solution adjacent to copper anodes.

Through an electrolysis process, pure copper is deposited onto the cathode plates from which it is subsequently removed through a mechanical
25 stripping process.

The use of wax on the edge of the cathode plates, is not an ideal barrier to unwanted copper growth for a number of reasons. Namely that it is easily removed during handling through scratching and bumping of the cathodes, thus permitting the growth of copper in locations where it must be manually removed,
30 and furthermore, some wax dissolves in the hot electrolyte solution causing a build up sludge in the refining tanks and a reduction in the life and efficiency of the electrolyte.

WO 97/41280

PCT/AU97/00246

2

Whilst the side edge protectors previously referred to operate effectively on the side edges of the plate, attempts to fit protectors to the bottom edge portion of the plate have met difficulties in the build up of copper in gaps at the corner of the plate as is best shown in Figure 2 of the drawings.

5 The thermal expansion of the edge protector creates small gaps at the joins and these gaps permit the growth of copper nodules beneath the edge protecting strip which defeats the prime purpose of the protecting strip and causes premature failure by mechanical failure through stretching of the legs of the strips.

10 It is an objective of the present invention to overcome at least some of the disadvantages of the prior art in providing a method and apparatus for protecting the edge portions of a cathode plate assembly destined to be immersed in electrolytic solution.

There is provided according to and aspect of the present invention a
15 method of protecting the edge portions of a cathode plate assembly useful for electrolytic deposition techniques, wherein the cathode plate is pre-fitted with bottom edge and side edge plastic strips, the plate and assembled edge strips being fitted into a plastic moulding apparatus such that the bottom edge portion corners of the plate are surrounded in the mould apparatus and comprising the
20 step of injecting plastic into the mould cavity to form moulded corner pieces integrally connected to the edge strips.

Conveniently, the plate is apertured or otherwise configured to form a locking engagement with the moulded corner pieces after flowing of the plastic during the corner moulding process.

25 There is provided according to a further aspect the present invention a corner moulding for a cathode plate adapted to interengage with side and bottom edge strips in which the moulding is preformed and adapted to be retained by clip means interconnecting the corner moulding and edge strips in sealing relationship with the cathode plate.

30 Conveniently the clip means comprises releasable clips adapted to interconnect said corner moulding and side moulding preferably in releasable relationship.

WO 97/41280

PCT/AU97/00246

3

Sealant may be injected into the assembled corner moulding to improve sealing between the moulding and the plate.

The plastic corner pieces are therefore mechanically locked and fixed to the plate, and restrain the edges of the edge strip from expanding during the high temperature deposition process.

In an alternative aspect of the invention, there is provided a method of protecting the edge and bottom portions of a cathode plate useful in electrolytic deposition techniques wherein edge portion strips destined to be fitted to the side and bottom edge portions of a cathode plate are joined in an assembled U configuration, plastic moulding of corner pieces to the joint between the bottom edge strip and at least one of the side edge strips prior to fitting of the edge strips to a cathode plate.

The invention will be described in greater detail having reference to the attached drawings in which Figures 1 and 2 represent prior art attempt at edge protection and Figures 3, 4 and 5 depict detailed sketches of the corner moulding technique of the present invention.

Figure 1 is a perspective view of an assembled corner mould without cathode plate.

Figure 7 is an exploded view of the components including the connecting clips.

With reference to the Figures, the cathode plate 10 made of stainless steel is conventionally hung from a horizontal hanging rail 11 which grips the top edge of the cathode plate wherein the cathode plate is adapted to be immersed in an electrolytic bath (not shown) which in copper or like non-ferrous metal.

To facilitate removal of the deposited metal from the cathode plate, after this process, it is desirable that the edges of the cathode plate are kept free of any deposited metal, so that after removal of the cathode plate from the bulk, the deposited metal can be easily removed from the surface of the plate.

Figure 1 shows a prior art method using side plastic edge strips 14 and a waxed bottom edge 15.

In some other arrangements, the side and bottom edges have wax applied thereto to prevent build up of deposited metal.

WO 97/41280

PCT/AU97/00246

4

With reference to Figure 2, this is a prior art attempt at forming mitred corners, together with bottom and side edge plastic strips fitted to the edge portions of the cathode plate.

Unfortunately, it has been found that the mitred corners tend to spread slightly due to differential thermal expansion between the cathode plate and the plastic edge protectors which allows ingress of electrolytic fluid onto the plate depositing copper underneath the edge protectors, and this tends to expand and damage the edge protectors and furthermore, creates difficulty in removing the deposited metal from the surface of the cathode plate.

Figures 3, 4 and 5 of the drawings depict a practical arrangement of the present invention in which the cathode plate 10 is apertured in the bottom corners thereof, and then fitted with edge protectors 11, 16 which may be of conventional form, along the side and bottom edge portions of the plate.

Subsequent to fitting of the edge protectors to the plate, the bottom corner regions of the plate are inserted into an injection mould and compatible molten plastic is allowed to fill the mould to form a moulded corner 17 integrally formed with the cathode plate 10 and the edge protectors 11, 16 as shown best in Figures 4 and 5.

It will be appreciated that such a moulding technique can be utilised with the edge protectors either fitted to the cathode plate or prior to fitting of the edge strips to the cathode plate.

The moulding of the corners to the edge strips in this embodiment includes the provision of an overlap in the joint between the edge and the corner mouldings 17 so that any thermal expansion of the plastic in the electrolyte bath is accommodated by the amount of overlap between the corner moulding and the edge strips, thus preventing any significant ingress of electrolytic material underneath the edge strips.

With reference to Figures 6 and 7 of the drawings, an alternative arrangement is disclosed.

WO 97/41280

PCT/AU97/00246

5

The cathode plate is provided with edge strips 20 as shown, which meet at each of the corners of the cathode plate. The corner moulding 21 is adapted to slide over each adjacent end of the edge strip 20 to cover the corner of the cathode plate. Upper and lower wedge clips 22 and 23 are adapted to snap fit into the edge strip and the corner moulding at each corner to retain the components effectively in sealing relationship. In this regard, the corner moulding is fabricated to be a snug fit over the adjacent ends of the edge strips 20 with the wedge clips 22 and 23 completing the enclosure of the adjacent ends of the edge strip to restrict ingress of material into the corner section of the cathode plate. The internal surfaces of the clip may be grooved as shown at 24 to receive a sealant such as silicone or similar elastomeric material which has been injected into the joint to improve sealing between the corner moulding and the edge clip.

Thus the present invention provides a useful alternative to the previous attempts at forming a clearly defined cathode plate edge free of any build up of electrolytic material.

WO 97/41280

PCT/AU97/00246

6

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A method of protecting the edge portions of a cathode plate assembly useful for electrolytic deposition techniques, wherein the cathode plate is prefitted with bottom edge and side edge plastic strips, the plate and assembled edge strips being fitted into a plastic moulding apparatus, such that the bottom edge portion corners of the plate are surrounded in the mould apparatus and comprising the step of injecting plastic into the mould cavity to form moulded corner pieces integrally connected to the edge strips.
2. A corner moulding for a cathode plate adapted to interengage with side and bottom edge strips in which the moulding is preformed and adapted to be retained by clip means, interconnecting the corner moulding and edge strips in sealing relationship.
3. A corner moulding as claimed in claim 2, wherein the clip means comprise releasable clips adapted to interconnect said corner moulding and side moulding preferably in releaseable relationship.
4. A clip means as claimed in claim 3, wherein the internal surface of the clip means is grooved to receive sealant injected into the assembled corner moulding to facilitate sealing between the moulding and the cathode plate.
5. A method of protecting the edge and bottom portions of a cathode plate useful in electrolytic deposition techniques, wherein edge portion strips destined to be fitted to the side and bottom edge portions of a cathode plate are joined in an assembled U configuration, plastic moulding of corner pieces to the joint between the edge strip and said side strips prior to fitting of the edge strips to the cathode plate.

WO 97/41280

PCT/AU97/00246

7

6. A method as claimed in claim 1 or claim 6 wherein the cathode plate is apertured or otherwise configured to form a locking engagement with the moulded corner pieces after flowing of the plastic moulding material during the corner moulding process.

WO 97/41280

PCT/AU97/00246

1/4

Fig 1.

Prior Art

Prior Art






Fig 2.

Prior Art





Detail A



Detail A

WO 97/41280

PCT/AU97/00246




WO 97/41280

PCT/AU97/00246

3/4


Fig 5.



WO 97/41280

PCT/AU97/00246

4/4



INTERNATIONAL SEARCH REPORT

International Application No.

PCT/AU 97/00246

A. CLASSIFICATION OF SUBJECT MATTERInt Cl⁶: C25D 11/00, C25C 7/02, C25D 17/10, B29D 12/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHEDMinimum documentation searched (classification system followed by classification symbols)
C25D 11/00, C25C 7/02, C25D 17/10, B29D 12/00, A47G 1/10, E06B 3/96Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
AU : IPC as aboveElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
(See attached sheet)**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	Derwent Abstract Accession No. 92-205388/25. Classes A28, M28, JP 04-136197 A2 (MITSUBISHI MATERIALS CORP) 11 May 1992 abstract	1, 5
X	Derwent Abstract Accession No. 83-812510/45, Class P27, NL 8201312 A (ALUART ALUMINIUM) 17 October 1983 abstract	2



Further documents are listed in the continuation of Box C



See patent family annex

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search 28 July 1997	Date of mailing of the international search report 05.08.97
Name and mailing address of the ISA/AU AUSTRALIAN INDUSTRIAL PROPERTY ORGANISATION PO BOX 200 WODEN ACT 2606 AUSTRALIA Facsimile No : (06) 285 3929	Authorized officer L.J. MENZ Telephone No.: (06) 283 2431

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/AU 97/00246

C (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 294170 A1 (NATIONAL PROFILES LIMITED) 7 December 1988 page 4, line 36 to page 6 line 12	2
A	US 4752350 A (SCHUSTER) 21 June 1988 column 1, line 49 to column 2, line 12	1
A	US 4670124 A (BARTSCH) 2 June 1987 column 3, line 65 to column 5 line 12	1-6
A	US 4207147 A (BABIN) 10 June 1980 column 1, lines 11 to 27	1-6
A	Derwent Abstract Accession No. 43415C/25, classes A85, M28, DD 140624T (VEB MANSFIELD-KOMB WILHEL) 19 March 1980 abstract	1-6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No.
PCT/AU 97/00246

This Annex lists the known "A" publication level patent family members relating to the patent documents cited in the above-mentioned international search report. The Australian Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent Document Cited in Search Report		Patent Family Member					
JP	4136197 A2						
NL	8201312 A	NL	183838 B	NL	183838 C		
AU	16971/88 A1	EP	294170 A1				
US	4752350 A	CA	1259159 A1	DE	3614673 A1		
US	4670124 A	AT	43367 E	AU	62097/86 A1	DE	3531176 A1
		EP	217429 A1	EP	217429 B1	ES	2001284 AF
		FI	863244 A	JP	62056590A2	PL	261217 A1
		ES	1000810 UA	ES	1000810 YA		
US	4207147 A	BE	871136 A1	CA	1082131 A1	DE	7829624 U1
		DE	2843279 A1	DE	2843279 C2	FR	2406008 A1
		FR	2406008 B1	IE	49616 B	JP	54074207A2
		JP	58022552B4	MX	146181 A		
DD	140624 T						
END OF ANNEX							

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/AU 97/00246

Electronic data base (continued)

Electronic Data BaseDERWENT.

SS 1: (C25B/IC OR C25C/IC OR C25D/IC OR C25F/IC)
 SS 2: 1 AND (ELECTROD: OR CATHOD: OR ANOD: OR POSIT: OR NEGAT: OR POLE: OR TERMIN:)
 SS 3: (B29D-012/00/IC)
 SS 4: (OPTIC: OR GLASS: OR SPECTAT:)
 SS 5: 3 AND NOT 4
 SS 6: 2 OR 5
 SS 7: 6 OR A47G-001/10/IC OR E06B-003/96/IC
 SS 8: 7 AND (PLAT: OR SHEET: OR PANEL: OR SLAB:)
 SS 9: 8 AND (EDG: OR BORD: OR RIM: OR SID:)
 SS 10: 9 AND (CORNER: OR BEND: OR ELBOW:)

JAPIO.

SS 1: (C25B/IC OR C25C/IC OR C25D/IC OR C25F/IC)
 SS 2: 1 AND (ELECTROD: OR CATHOD: OR ANOD: OR POSIT: OR NEGAT: OR POLE: OR TERMIN:)
 SS 3: (B29D-012/00/IC)
 SS 4: (OPTIC: OR GLASS: OR SPECTAT:)
 SS 5: 3 AND NOT 4
 SS 6: 2 OR 5
 SS 7: 6 OR A47G-001/10/IC OR E06B-003/96/IC
 SS 8: 7 AND (PLAT: OR SHEET: OR PANEL: OR SLAB:)
 SS 9: 8 AND (EDG: OR BORD: OR RIM: OR SID:)
 SS 10: 9 AND (CORNER: OR BEND: OR ELBOW:)